

# FASTSET™ WATER-STOP CEMENT

PRODUCT No. 1126-28

## PRODUCT DESCRIPTION

QUIKRETE® FastSet™ Water-Stop Cement is a high performance, rapid setting, high strength repair material designed to instantly stop flowing water from cracks or holes in concrete or masonry walls, above and below grade.

## PRODUCT USE

QUIKRETE® FastSet™ Water-Stop Cement will block running water when application is made to masonry or concrete. This special formulation allows the product to obtain high strength and rapid set while repelling water. QUIKRETE® FastSet™ Water-Stop Cement solves leakage problems wherever active water is present, in all masonry and concrete above and below grade. Use QUIKRETE® FastSet™ Water-Stop Cement for sealing around concrete pipes and for plugging leaks in:

- Foundation and retaining walls
- Chimneys
- Swimming pools, fountains, and cisterns

## SIZES

- 20 lb (9 kg) pails

## YIELD

- Each 20 lb (9 kg) bag of QUIKRETE® FastSet™ Water-Stop Cement will yield approximately 290 in<sup>3</sup> (4.75 L) of mixed concrete.

## TECHNICAL DATA

### APPLICABLE STANDARDS

- ASTM C109 Standard Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or [50-mm] Cube Specimens)
- ASTM C191 Standard Test Method for Time of Setting of Hydraulic Cement by Vicat Needle

### PHYSICAL/CHEMICAL PROPERTIES

Typical results obtained for QUIKRETE® FastSet™ Water-Stop Cement, when tested in accordance with the referenced ASTM procedures, are shown in Table 1.

TABLE 1 TYPICAL PHYSICAL PROPERTIES

Setting Time, ASTM C191	
Final	60 to 90 seconds after mixing
Compressive Strength, ASTM C109 (Modified)	
Age	PSI (MPa)
2 hours	1000 (6.8)
24 hours	2500 (17.2)
7 days	4500 (31.0)
28 days	5500 (37.9)

## DIVISION 3 & 7

03 01 00 Maintenance of Concrete  
07 16 00 Cementitious  
Dampproofing



## INSTALLATION SURFACE PREPARATION

All repair areas should be free of loose material, dirt, dust, algae, and mildew and any paint, sealant, or other non-cementitious coating. Preparation should include enlarging small cracks and holes. Edges must be square or undercut; avoid V-shape cuts.



## MIXING

Mix only the amount of QUIKRETE® FastSet™ Water-Stop Cement that can be applied in 1 minute after mixing. Add powder to water to blend 4-1/2 parts of QUIKRETE® FastSet™ Water-Stop Cement with 1 part potable water by volume, until a heavy putty consistency is achieved. Quickly roll the mixture between your gloved hands to mix. In most cases, limit batch size to 4 to 6 oz (113 to 170 g) of powder. Using 4-1/2 oz (128 g) of powder and 1 oz (28 g) of water will provide a golf ball size mix, which is appropriate for most applications.

## APPLICATION

Starting at the top of the crack and working down, apply QUIKRETE® FastSet™ Water-Stop Cement while maintaining light pressure on the patch. Maintain pressure until initial set begins and the leaking is stopped. If more than one application is needed to fill the active leak, each application must be made before the prior one has set completely. Excess material can be removed to form a smooth surface.

## **CURING**

No special curing methods, such as membranes or compounds are required.

## **PRECAUTIONS**

- Mix no more than can be placed in 1 minute after mixing.
- Hot temperatures will reduce the setting time. At colder temperatures, below 50 °F (10 °C), use warm water.
- Product is only for use to fill active leaks in cracks or holes; it is not for application to flat surfaces. Not for resurfacing or coating a wall.
- If more than one application is needed to repair the active leak, each application must be made before the prior one has set completely.
- When making repairs, good color matching can be difficult. Preview a small quantity of the material in an inconspicuous area and allow it to cure before evaluating color and overall appearance.
- This material is reactive and may degrade unpainted aluminum.

## **SAFETY**

**IMPORTANT:** Read Safety Data Sheet carefully before using. **WEAR IMPERVIOUS GLOVES**, such as nitrile, mask, and eye protection.

**DANGER:** Causes sever skin burns and serious eye damage. Prolonged or repeated inhalation of dust may cause lung damage or cancer.

**KEEP OUT OF REACH OF CHILDREN**

## **WARRANTY**

**NOTICE:** Obtain the applicable **LIMITED WARRANTY** at [www.quikrete.com/product-warranty](http://www.quikrete.com/product-warranty) or send a written request to The Quikrete Companies, LLC, Five Concourse Parkway, Atlanta, GA 30328, USA. Manufactured by or under the authority of The Quikrete Companies, LLC. © 2022 Quikrete International, Inc.